

# APM-PRO™ Typical Performance Data

## Test Results for APM PRO

Test	ASTM #	Result
Acid No., mg KOH/g oil	D664	1.2
Copper Strip Corrosion, 2 hours at 100°C	ASTM D130	1A
Flash Point (COC), °C	ASTM D92	170
Pour Point, °C	ASTM D97	-24
Rust Preventive Characteristics	ASTM D665	Pass
Viscosity	ASTM D445	
@ 100°C		7.2
@ 40°C		67.5
@ 10°C		528
@ 0°C		946
@ -40°C		Solid
Falex 4 Ball 20kgf, 60 min, 75°C Wear Scar in mm	ASTM D4172	0.53 See note 1

*Note 1 - This test was carried out with 6% APM Pro in 10W30 engine oil. All of the other tests listed in the table were carried out on the undiluted APM Pro.*

Test Date: April 2013 • Test Lab: Powertech Labs Inc.